

## AMENDMENTS TO THE CLAIMS

1. (Currently amended) A method of fabricating a steel part, the method comprising the steps of:

- preparing and casting a steel consisting essentially of the following composition in percentage by weight:  $0.06\% \leq C \leq 0.25\%$ ;  $0.5\% \leq Mn \leq 2\%$ ;  $traces \leq Si \leq 3\%$ ;  $traces \leq Ni \leq 4.5\%$ ;  $traces \leq Al \leq 3\%$ ;  $traces \leq Cr \leq 1.2\%$ ;  $traces \leq Mo \leq 0.30\%$ ;  $traces \leq V \leq 2\%$ ;  $traces \leq Cu \leq 3.5\%$ ;  $0.005\% \leq S \leq 0.2\%$ ; 5 ppm to 50 ppm of B, 0.005% to 0.04% of Ti, where the Ti content is equal to at least 3.5 times the N content of the steel;

- at least one of the following elements: Ca up to 0.007%; Te up to 0.03%; Se up to 0.05%; Bi up to 0.05%; and Pb up to 0.1%, and

- wherein the steel satisfies at least one of the following conditions:

- \*  $0.5\% \leq Cu \leq 3.5\%$ ;

- \*  ~~$0.5\% \leq V \leq 2\%$~~ ;

- \*  $2\% \leq Ni \leq 4.5\%$  and  $1\% \leq Al \leq 2\%$ ;

the remainder being iron and impurities resulting from preparation;

- hot deforming the cast steel at least once at a temperature in the range 1100°C to 1300°C in order to obtain a blank of the part;

- controlled cooling of the blank for the part in still air or forced air to obtain a bainite microstructure; and

- heating the steel to perform precipitation annealing before or after machining the part from said blank,

- wherein the hot deformation is forging;

- wherein when the steel satisfies the condition regarding Cu, the precipitation annealing is performed in the range of 425°C to 500°C for 1 h to 10 h, ~~when the steel satisfies the condition regarding V, the precipitation annealing is performed in the range of 500°C to 600°C for more than 1 h,~~ and when the steel satisfies the condition regarding Ni and Al, the precipitation annealing is performed in the range of 500°C to 550°C for more than 1 h;

- wherein the controlled cooling of the blank is performed at a rate less than or equal to 3°C/s in the range of 600°C to 300°C,

- wherein the part has a ~~tensile~~tensile strength Rm of 1000 MPa to 1300 MPa, and a yield strength Re of greater than or equal to 900 MPa, and

- wherein the bainite microstructure obtained after controlled cooling of the blank is 100% bainite.

2-4. (Cancelled)

5. (Currently amended) A method of fabricating a steel part, the method comprising the steps of:

- preparing and casting a steel consisting essentially of the following composition in percentage by weight:  $0.06\% \leq C \leq 0.25\%$ ;  $0.5\% \leq Mn \leq 2\%$ ;  $traces \leq Si \leq 3\%$ ;  $traces \leq Ni \leq 4.5\%$ ;  $traces \leq Al \leq 3\%$ ;  $traces \leq Cr \leq 1.2\%$ ;  $traces \leq Mo \leq 0.30\%$ ;  $traces \leq V \leq 2\%$ ;  $traces \leq Cu \leq 3.5\%$ ;  $0.005\% \leq S \leq 0.2\%$ ; 0.005% to 0.06% of Nb; 5 ppm to 50 ppm of B, 0.005% to 0.04% of Ti, where the Ti content is equal to at least 3.5 times the N content of the steel;

- at least one of the following elements: Ca up to 0.007%; Te up to 0.03%; Se up to 0.05%; Bi up to 0.05%; and Pb up to 0.1%, and

- wherein the steel satisfies at least one of the following conditions:

- \*  $0.5\% \leq Cu \leq 3.5\%$ ;

- \*  ~~$0.5\% \leq V \leq 2\%$~~ ;

- \*  $2\% \leq Ni \leq 4.5\%$  and  $1\% \leq Al \leq 2\%$ ;

- the remainder being iron and impurities resulting from preparation;

- hot deforming the cast steel at least once at a temperature in the range 1100°C to 1300°C in order to obtain a blank of the part;

- controlled cooling of the blank for the part in still air or forced air to obtain a bainite microstructure; and

- heating the steel to perform precipitation annealing before or after machining the part from said blank,

- wherein the hot deformation is forging;

- wherein when the steel satisfies the condition regarding Cu, the precipitation annealing is performed in the range of 425°C to 500°C for 1 h to 10 h, ~~when the steel satisfies the condition regarding V, the precipitation annealing is performed in the range of 500°C to 600°C for more than 1 h,~~ and when the steel satisfies the condition regarding Ni and Al, the precipitation annealing is performed in the range of 500°C to 550°C for more than 1 h;

- wherein the controlled cooling of the blank is performed at a rate less than or equal to 3°C/s in the range of 600°C to 300°C,

- wherein the part has a ~~tensil~~-tensile strength Rm of 1000 MPa to 1300 MPa, and a yield strength Re of greater than or equal to 900 MPa, and

wherein the bainite microstructure obtained after controlled cooling of the blank is 100% bainite.

6-7. (Cancelled)

8. (Previously presented) The method according to claim 1, wherein the C content of the steel lies in the range 0.06% to 0.20%.

9. (Previously presented) The method according to claim 8, wherein Mn content of the steel lies in the range 0.5% to 1.5%, and wherein the Cr content lies in the range 0.3% to 1.2%.

10. (Previously presented) The method according to claim 8, wherein the Ni content of the steel lies in the range traces to 1%.

11. (Previously presented) The method according to claim 8, wherein the Ni content of the steel lies in the range 2% to 4.5%, and wherein the Al content lies in the range 1% to 2%.

12-18. (Cancelled)

19. (Original) A steel part, obtained by the method according to claim 1.

20-21. (Cancelled)

22. (Currently amended) The method according to claim 1, wherein the ~~conditions~~ condition regarding V, Ni and Al ~~are~~ is not satisfied, and therefore the steel satisfies the condition regarding Cu, and the precipitation annealing is performed in the range of 425°C to 500°C for 1 h to 10 h.

23. (Cancelled)

24. (Currently amended) The method according to claim 1, wherein the ~~conditions~~  
condition regarding Cu ~~and V are~~is not satisfied, and therefore the steel satisfies the  
condition regarding Ni and Al, and the precipitation annealing is performed in the range  
of 500°C to 550°C for more than 1 hr.